



Consolideck® PolishGuard Stain Resistance Testing Summary

For PROSOCO, Inc.

December 2010

AMT Laboratories • 3741 Greenway Circle • Lawrence, Kansas 66046 • (888) 376-3600

TEST METHODS: Stain Resistance – ASTM D 1308

The treatment was applied in accordance with PROSOCO, Inc. Product Data Sheet instructions and allowed to cure for 7 days prior to testing. The soiling agents were allowed to dwell on the treated substrate for 15 minutes, 1 hour, and 4 hours. Evaluation consisted of a visual examination of the tested areas to determine the effect the reagent had on the sample using the following scale:

E = Excellent (No Adverse Effects)

G = Good (Limited Adverse Effects)

F = Fair (Moderate Adverse Effects)

P = Poor (Unsatisfactory)

Polished Concrete

Acids	PolishGuard			Underlying Substrate			Bases	PolishGuard			Underlying Substrate		
	15 min	1 hr	4 hr	15 min	1 hr	4 hr		15 min	1 hr	4 hr	15 min	1 hr	4 hr
10% Citric	E	E	E	E	E	E	5% Ammonium Hydroxide	E	E	E	E	E	E
10% Acetic	E	E	G	E	E	E	30% Ammonium Hydroxide	E	E	E	E	E	E
10% Oxalic	E	E	E	E	E	E	10% Potassium Hydroxide	E	E	E	E	E	E
10% Hydrochloric	E	E	E	E	E	E	45% Potassium Hydroxide	E	E	E	E	E	E
35% Hydrochloric	P	P	P	F	F	F	10% Sodium Hydroxide	E	E	E	E	E	E
10% Phosphoric	P	P	P	F	F	F	50% Sodium Hydroxide	E	E	E	E	E	E
70% Phosphoric	G	P	P	G	F	F	Solvents						
10% Sulfuric	E	E	G	E	E	E	Acetone	P	P	P	E	E	E
50% Sulfuric	E	E	E	E	E	E	Mineral Spirits	E	E	E	E	E	E
Alcohols							Xylene	E	E	E	E	E	E
Benzyl Alcohol	P	P	P	E	E	E	Hydraulic Fluids / Oils / Fuels						
Ethyl Alcohol	E	E	E	E	E	E	Gasoline	E	E	E	E	E	E
Isopropyl Alcohol	E	E	E	E	E	E	Brake Fluid	E	E	E	E	E	E
Ethylene Glycol	E	E	E	E	E	E	Motor Oil	E	E	E	E	E	E
Salts							Automatic Trans. Fluid	E	E	E	E	E	E
Calcium Chloride	E	E	E	E	E	E	Skydrol	G	F	F	E	E	E
Sodium Bicarbonate	E	E	E	E	E	E	Other Chemicals / Misc.						
Sodium Chloride	E	E	E	E	E	E	Cola	E	E	E	E	E	E
							Mustard	E	E	E	E	E	E
							Ketchup	E	E	E	E	E	E
							Red Wine	E	E	E	E	E	E
							Balsamic Vinegar	E	E	E	E	E	E
							Vegetable Oil	E	E	E	E	E	E
							Bleach	E	E	E	E	E	E
							Tap Water	E	E	E	E	E	E
							Laundry Detergent (Tide)	E	E	E	E	E	E
							Lemon Juice	E	E	E	E	E	E

Test results were obtained under laboratory conditions. Reasonable variations can be expected due to environmental conditions, etc.